



ELEVATION - 6' SCREENING WALL AND PIERS





WALL PANEL CAP - PLAN VIEW & ELEVATION




DETAILS - OLDBRICK WALL PANEL & CAP

*** NOTE OLDBRICK STYLE PATTERN NOT EXACT ***






WALL PANEL CAP - SECTION



SECTION - 6' SCREENING WALL AND PIER LINE POST PIER

LINE POST PIERS WILL HAVE NO REBAR



SECTION - 6' SCREENING WALL AND PIER END POST PIER

END POST PIERS WILL HAVE REBAR. END POST PIERS ARE DESIGNATED AS THE FIRST THREE POSTS AT THE END OF THE WALL.

Specifications and Notes

- 1. This project has been designed in accordance with the International Building Code, 2010 Edition.
- a, Wind Velocity (V) = 90 mph
- b. Exposure: B
- c. Importance Factor (I) = 1.0 d. Velocity Pressure Exposure Coefficient (Kz) = 0.70
- f. Topographic Factor (Kzt) = 1.0g. Wind Pressure $P = 0.00256(Kz)(Kzt)(Kd)(V^2)(I)$ $P = 0.00256(0.70)(1.0)(0.85)(90)^2(1.0)$ P = 12.3 psf
- h. Working Design Stress: 33% Increase (1.33) i. Seismic Design: Site Class D
- Precast components to be manufactured by Artisan Precast a. Posts, Panels and Panel caps shall be precast off-site.
- Screening wall is to be erected entirely on the project property
- c. Piers/Footings are to be cast in place on site.

- 1. Concrete Materials:
- a. Concrete shall be normal weight concrete having sand and gravel or crushed stone aggregate. Mixed with ASTM-C150, type | or ||| portland cement to meet the

- 1. panels & post: 5000 psi @ 28 days 2. footings & piers: 3000 psi @ 28 days 3. sidewalk & non-structural: 3000 psi @ 28 days b. Water used for concrete shall be clean water and free from injurious amounts of oils, acids, alkalites, organic or other celeterious substances
- All concrete permanently exposed to the weather shall contain an air—entraining admixture resulting in 3 to 6 percent entrained air or recommended by the
- Concrete workmanship:
 a. Fresh poured concrete shall be tamped in to place using
- concrete is thoroughly compact and without void.
 b. Excavation for footing shall be on undisturbed soil or to the depth noted on the drawings. Leave the bottom bearing surface clean and smooth. If faoting excavations are made deeper than intended, only concrete shall be used for fill. Remove all loose material from excavations prior to concrete pour.

- Deformed type bars shall conform to ASTM—A 615, Grade 60 placed as shown on the drawings.
- Steel reinforcing wire shall meet U.S. Steel Wire gauge, ASTM-A 82. fy = 70,000 psi min galvanized.
 All ties and stirrups shall conform to the
- requirements of ASTM-A/ 615, grade 40.
- d. All welded wire reinforcement shall be 4x12-D4/D4 having 3 horizontal bars and 5 vertical bars.
- 2. Reinforcing workmanship:
- Reinforcement steel shall be fabricated in accordance with the CRSI Standard Detail.
 Reinforcing bars shall be cold—bent only. Use of heat to bend reinforcement steel shall be
- cause for rejection.
 b. Reinforcement steel bars and wire fabric shall be thoroughly cleaned before placing and again before the concrete is placed. Shall be accurately positioned and secured in place. No brick of porous materials may be used to support the steel off the
- c. Install all reinforcement with the following clearance between reinforcing steel and face of concrete:
 - 1. Footing, pier or beam bottom (3")
 - 2. Earth—formed pier or beam side (2")
 3. Formed footing, pier or beam sides, exposed (1")
 - Precast exposed to weather: panels (3/4"), posts (1-1/4")
- d. Splices within continuous unscheduled reinforcing
- steel shall have a minimum lap of 30 bar diameters.

- 1. Footing size is based on the following minimum
- a. Soil Compaction ******* 90% std. proctor
- b. Bearing Capacity ******* 1,500 psf c. Friction Resistance ****** 260 psf d. Lateral Bearing ******* 100 psf/ft of depth

1. All design criteria based on construction on natural ground. Screenwall not to be constructed on berms or fill dirt.



HILLTOP CONCRETE
18775 FM 2493
FLINT, TX 75762
(903) 630-5465 OLDBRIC 18775 F FLINT, ' (903) 6

